

**T D S****MICA TAPE - RESIN POOR (VPI) WITH ACCELERATOR**

TYPE : C4331

Page No: 1

Item		Unit	C4331-1C				C4331-1CP		
Nominal Thickness		mm	0.13	0.14	0.15	0.16	0.13	0.14	
Thickness Tolerance	Average	mm	±0.02						
	Individual		±0.03						
Weight of Tape		g/m <sup>2</sup>	197±14	206±14	220±18	233±18	205±14	212±14	
Mica Content		g/m <sup>2</sup>	160±12	160±12	180±14	180±14	160±12	160±12	
Polyester Film		g/m <sup>2</sup>	-	-	-	-	35±3	42±4	
Glass Cloth		g/m <sup>2</sup>	20±2	28±2	20±2	32±2	-	-	
Binder Content		%	5-11	5-11	5-11	5-11	≤10	≤10	
Volatile Content		%	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	
Dielectric Strength		Kv/mm	≥10	≥10	≥10	≥10	≥40	≥50	
Tensile Strength		N/cm	≥60	≥100	≥60	≥100	≥30	≥40	
Catalyst Zinc Naphtenate		Mg/m <sup>2</sup>	450±120						
Test Method			IEC 371-2						

