

**T D S****MICA TAPE-RESIN RICH**

TYPE : C4332

(PAGE 1)

Item		Unit	C4332-1	C4332-1A	C4332-1P	
Nominal Thickness		mm	0.14	0.13	0.12	0.14
Thickness Tolerance	Average	mm	±0.02	±0.02	±0.02	±0.02
	Individual		±0.03	±0.03	±0.03	±0.03
Weight of Tape		g/m <sup>2</sup>	195±15	205±15	200±10	200±15
Mica Content		%	≥37	≥65	≥38	≥37
Polyester Film		g/m <sup>2</sup>	-	-	28±3	35±3
Polyimide Film		g/m <sup>2</sup>	35±3	35±3	-	-
Glass Cloth		g/m <sup>2</sup>	20±2	-	20±2	20±2
Binder Content		%	25-32	≥12	30-38	26-34
Volatile Content		%	≤4.0	≤2.0	≤3.0	≤2.0
Dielectric Strength		Kv/mm	≥40	≥35	≥45	≥45
Tensile Strength		N/cm	≥60	≥30	≥60	≥60
Test Method		IEC 371-2				