

T D S**MICA TAPE-RESIN RICH**

TYPE : C4332

(PAGE 2)

Item	Unit	C4332-1C	C4332-1D	C4332-1E	C4332-1F	C4332-1G	
Nominal Thickness	mm	0.11	0.16	0.14	0.22	0.18	
Thickness Tolerance	Average	mm	±0.02	±0.02	±0.02	±0.025	±0.02
	Individual		±0.03	±0.03	±0.03	±0.035	±0.03
Weight of Tape	g/m ²	170±12	225±15	205±15	360±20	335±15	
Mica Content	%	≥45	≥34	≥37	≥40	≥45	
Polyester Film/ Polyester Shrinkable Film	g/m ²	(17±2) x 2	-	-	28±3	55±5	
Polyimide Film	g/m ²	-	35±3	-	-	-	
Glass Cloth	g/m ²	18±2	(20±2) x2	(20±2) x2	(20±2) x2	20±4	
Binder Content	g/m ²	16-24	24-33	≥36	30-38	25-32	
Volatile Content	%	≤2.0	≤5.0	≤2.0	≤3.0	≤2.0	
Dielectric Strength	KV/mm	≥45	≥40	≥24	≥30	≥40	
Tensile Strength	N/cn	≥60	≥100	≥80	≥100	≥60	
Test Method	IEC 371-2						