

T D S**MICA TAPE - RESIN POOR (VPI) WITHOUT ACCELERATOR**

TYPE : C4331

Page No: 2

Item	Unit	C4331-1A				C4331-1B			C4331-1BG	
		0.13	0.14	0.15	0.16	0.10	0.13	0.14	0.15	0.16
Nominal Thickness	mm	0.13	0.14	0.15	0.16	0.10	0.13	0.14	0.15	0.16
Thickness Tolerance	Average	±0.02								
	Individual	±0.03								
Weight of Tape	g/m ²	197±14	206±14	220±18	233±18	165±12	205±14	212±14	218±16	235±16
Mica Content	g/m ²	160±12	160±12	180±14	180±14	120±10	160±12	160±12	160±12	160±12
Polyester Film	g/m ²	-	-	-	-	35±3	35±3	42±4	21±2	35±3
Glass Cloth	g/m ²	20±2	28±2	20±2	32±2	-	-	-	20±2	20±2
Binder Content	%	5-11	5-11	5-11	5-11	≤10	≤10	≤10	≤10	≤10
Volatile Content	%	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0	≤1.0
Dielectric Strength	Kv/mm	≥10	≥10	≥10	≥10	≥40	≥40	≥50	≥40	≥40
Tensile Strength	N/cm	≥60	≥100	≥60	≥100	≥30	≥30	≥40	≥60	≥60
Test Method	IEC 371-2									