



T D S

PHLOGOPITE MICA PE BACKED TAPE

TYPE: CP 25 H

Item	Unit	THICKNESS	
		0.10 mm	0.135 mm
Appearance		No foreign material, No marks , Surface is smooth	
Width	mm	6 ~ 1000	
Length	m	500m, 1000m (Above 1000 m in spool package)	
Thickness	mm	0.10 ± 0.015	0.135 ± 0.015
Weight of Tape	g/m ²	140 ± 10	205 ± 15
Weight of mica paper	g/m ²	100 ± 5	168 ± 5
Weight of Polyethylene Film	g/m ²	24 ± 2	24 ± 2
Binder content	%	8 ± 3	8 ± 3
Breakdown Voltage	KV/ Layer	> 5.5	> 6
Tensile Strength	N/15mm	> 130	> 130
Mica content	%	> 65	> 75
Fire Grade	°C	950°C ~ 1000°C (IEC60331/BS6387)	
Test Procedure		IEC371-2	

* We can change weight of mica paper as per your requirement

Representative

Chhaperia International Co.
 Plot 270, 4th Phase, Peenya Industrial
 Area, Bangalore - 560 058. India
 Ph. : +91 80 41171552 / 28362823
 Fax : +91 80 28360371 / 28396999
 E-mail : info@micagroup.net
 www.micagroup.net